



TECHNICAL DATASHEET DRAFT

SAP No. 20007540 Article Description B-S-E-SFUP-1627g/m²-1524mm

Textile Structure 7006816 SAERfix® UP

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

Layer	Construction	Areal weight	Tolerance	Material
4	0 °	567 g/m ²	+/- 5.0 %	E-glass 2,400 TEX
3	90 °	566 g/m ²	+/- 5.0 %	E-glass 2,400 TEX
2	CFM	450 g/m ²	+/- 10.0 %	HUN M8635D2
1	Glue	8 g/m ²	+/- 16.0 %	SAERfix UP
Stitching		18 g/m ²	+/- 3 g/m ²	PES [Polyester] 167 dtex
Stitching 2		18 g/m ²	+/- 3 g/m ²	PES [Polyester] 167 dtex

Fiber input can be determined individually

FURTHER CHARACTERISTICS

Gauge	7.0	Stitching pattern	tricot	Width (nominal)	1,524 mm
		Stitching pattern 2	warp		
Stitch length	4.00 mm	Total tolerance	6.5 %	Total areal weight	1627 g/m ²

Labelling (Standard) Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

Storage With original packaging: No moisture recommendation and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.